

## AXPOLY® PP51 1032

**Product information sheet:** Black copolymer polypropylene resin grade, 20% filled

**Description:** A 20% mineral filled PP grade that delivers greater stiffness in moulded components, plus a higher flexural modulus where stability under load is important.

### Product physical properties

Product grade: Axpoly® PP51 1032, 20% filled

Test parameter	ISO standard	Mean value	Units
MFI (2.16 kg @ 230°C)	1133	7	g/10mins
Density	1183 -1	1.00	g/cm <sup>3</sup>
Tensile strength	527 - 1/2	19	MPa
Impact strength	180	5	kJ/m <sup>2</sup>
Elongation @ break	527 - 1/2	15	%
Flexural Modulus	178	1400	MPa

**Please note** this polymer is not approved for use in food, medical or toy applications.



[www.axiongroup.co.uk/AxpolyPolypropylene](http://www.axiongroup.co.uk/AxpolyPolypropylene)

Indigo Street, Off Langley Road South, Salford. M6 6RX  
 Tel. +44 161 737 6124  
 E. [info@axionpolymers.com](mailto:info@axionpolymers.com)